


Eagle Engineering PE1000 Material relative abrasion values

| Material | Relative Abrasion |
|----------|-------------------|
| Alum | 1500 |
| POM | 1100 |
| PET | 900 |
| PP | 750 |
| PVDF | 750 |
| PTFE | 500 |
| PE 500 | 400 |
| Steel | 262 |
| S.Steel | 242 |
| PE1000 | 100 |

Eagle Engineering (Telford) Ltd
 Unit D3 Haybrook industrial estate
 Halesfield 9
 Telford
 TF7 4QW
 Tel: +44 (0) 1952 586478



The chart above demonstrates the lower the relative abrasion rate the higher the wear resistance of the material. For example, PP (polypropylene) deteriorates 7.5 times faster than PE1000.